



CLIMATIZER PLUS Cellulose Fiber Insulation Technical Data Sheet

| Ver012-07222026

SPECIFICATIONS	CLIMATIZER PLUS CELLULOSE INSULATION
Packaging	30 lbs/13.61kg transparent bag
Product Identifier	Cellulose Fibre Insulation (CFI)
Product Type	Loose-fill Thermal and Acoustical insulation
Description	Fiberized paper treated with fire retardants
Design Density	Attics: 24.9kg/m ³ 1.6lb/cu.ft
Manufacturer	Climatizer Insulation Inc. 120 Claireville Drive, Etobicoke ON M9W5Y3 t: 416-798-1235 f: 416-798-1311 Office hours: Mon-Fri 8am-5pm info@climatizer.ca orders@climatizer.ca www.climatizer.ca

Description

CLIMATIZER PLUS™ is a loose-fill fibrous insulation made from specially selected paper stock, which is chemically treated with non-toxic additives to enhance fire resistance, as well as protect against pests and moisture. This product is manufactured in a controlled environment that adheres to a strict Quality Management System. Additionally, Climatizer Plus CFI is featured in an industry-wide cellulose Environmental Product Declaration, available on our website.

Composition

CLIMATIZER PLUS™ is manufactured from selected organic and recycled fibres that are impregnated with additives to results moisture, mould, wood decay, insects, vermin, corrosion and combustion. Forumula includes the following materials:

Cellulose Fibres (recycled paperstock): $C_6H_{10}O_3$

Boric Acid: H_3BO_3

Ammonium Sulphate: $(NH_4)_2SO_4$

Requirement Standards

CLIMATIZER PLUS™ is manufactured to meet requirements based on the following standards: 1. Canadian Construction Materials Centre (CCMC) "Standards for Cellulose Fibre Insulation (CFI) for Buildings CAN/ULC S703-09; and, 2. CCMC Evaluation Listing 09217-L

Application

CLIMATIZER PLUS™ is a loose-fill or spray applied thermal and acoustical insulation. Loose-fill is appropriate for horizontal or moderately sloped attic areas up to 4:12 pitch. Injection may be



CLIMATIZER PLUS Cellulose Fiber Insulation

Technical Data Sheet

| Ver012-07222026

used to fill areas such as flat or sloped ceiling and vertical walls. Spray applied may be used in open stud cavities or steeply sloped attic surfaces. Choose the most appropriate method of installation to achieve the desired or thermal and/or acoustical performance. CLIMATIZER PLUS™ can be used in new construction or to retrofit existing structures/dwellings.

Limitations

Like other insulation types, CLIMATIZER PLUS™ should not be placed in direct contact with heat sources such as chimney flues, electric motors or light fixtures. Unless CSA approved for use with thermal insulation, do not cover recessed light fixtures with any type of insulation as excessive heat build-up may occur. An air space of 6" or more is required between the fixture and its protective barrier. This consideration also applies to any other heat source such as fan motors, transformers, or incandescent trouble lights. Similarly, do not permit insulation to directly cover a chimney or flue. Do not fill fireplace or furnace chases. Maintain the minimum clearance specified by the building code or inspector having jurisdiction. CLIMATIZER PLUS™ should not be used where the ambient temperature is continuously above 90°C (or 194°F).

Technical Data

CAN/ULC Test Criteria:	CAN/ULC S703-09	Fungal Growth:	Passed
CAN/ULC S102	FSC 20	Limited Design Density (Type 1	
CAN/ULC S102.2	FSC 120	Open Spaces:	27.23km/m ³
Open Flammability (Permanence):	Passed	Corrosiveness:	Passed
Open Flammability (W/cm2):	Passed	Smoulder Resistance:	Passed
Moisture Vapour Absorption:	Passed	Thermal Resistivity:	Passed

Thermal Resistance Comparison

The following values for thermal resistance of cellulose insulation at seasonal temperature extremes were taken from the ASHRAE Handbook of Fundamentals (Re: BNL50862):

Winter Value at 5°C	RSI 0.678 (R 3.85)
Design Value at 24°C	RSI 0.652 (R 3.70)
Summer Value at 43°C	RSI 0.629 (R 3.57)

The above value indicated the change in CLIMATIZER PLUS™ R-value between winter and summer attic temperatures is only 7.1%, whereas a continuation of the tables for other types of insulation indicates the R-value loss for mineral fibre under the same circumstances would be 21.4%.

Acoustical Properties

CLIMATIZER PLUS™ offers superior qualities for improving noise suppression in wall, floor or ceiling construction. There are 4 primary factors to consider: Mass; Dampening; Absorption; and Sealing.

1. Mass (Density): Increased mass per unit of thickness of CLIMATIZER PLUS™ compared to other types of insulation adds to the overall effectiveness of a wall, floor or ceiling assembly in improving STC (Sound Transmission Class) value.



CLIMATIZER PLUS Cellulose Fiber Insulation

Technical Data Sheet

| Ver012-07222026

2. Dampening: Unlike fibrous batts or foam boards, CLIMATIZER PLUS™ incorporates itself as an integral part of a wall, floor or ceiling assembly. The natural ability of CLIMATIZER PLUS™ to fill crevices and gaps produces a significant improvement in the sound dampening characteristics of the assembly.

3. Absorption: CLIMATIZER PLUS™, because of the unique porosity of its interwoven fibres, will exhibit a NRC (Noise Reduction Coefficient) of 0.75 at a 25 mm (1inch) thickness. Increased attenuation in both low and high absorption within an enclosed wall or ceiling cavity.

4. Sealing: The field reliability of CLIMATIZER PLUS™ natural noise reduction capabilities are realized through its natural ability to fill crevices and voids normally occurring in wall, floor, ceiling or attic construction. When installed correctly and according to applicable Building Codes, CLIMATIZER PLUS™ will provide a comprehensive seal around complex shapes and structures thereby ensuring its ability to minimize sound transmission through such space interruptions.

Filtration Properties

CLIMATIZER PLUS™ offers the added advantage of keeping a home cooler during the summer season. There is a natural movement of air either by convection currents of air from warm to cold environments or movement by pressure differentials. CLIMATIZER PLUS™, due to its perfect fit and greater mass, inhibits this air movement. Other types of insulation may offer a poor fit and in testing have shown to lose up to half their insulation values. In retrofit conditions where additional attic insulation is desired, CLIMATIZER PLUS™ can be used as a blanket cover to significantly reduce air movement, fill gaps in existing insulation (despite type), and between the insulation and adjacent framing members. This can substantially increase the overall insulation value.

Thermal Resistance vs. Applied Bulk Density

CLIMATIZER PLUS™ maintains an almost constant R-value over the full range of densities at which it can be installed, whereas light density glass fibre loose-fill insulation suffers a drastic loss in R-value if the density is only slightly less (fluffing) than the required density.

Fire Resistance

CLIMATIZER PLUS™ exhibits fire resistance capabilities identified in the physical properties chart. It will not melt or degrade as most other insulation types will when exposed to flame or high temperatures. Because it will only char under direct fire exposure, it can provide heat protection longer to adjacent building materials, and therefore allow building occupants more time to escape than would many other insulation materials.

Moisture

CLIMATIZER PLUS™ is able to dissipate excess moisture and maintain a moderate range in moisture content. Canadian homes and buildings can experience a loss of warm moist air from the interior environment to the colder exterior air by several means such as unsealed, torn, or discontinuous vapour



CLIMATIZER PLUS Cellulose Fiber Insulation

Technical Data Sheet

| Ver012-07222026

barrier, or by piping or electrical wiring boxes penetrating the vapour barrier. During the heating season, these disruptions to the vapour barrier permit moisture to the insulation layer or on the cold roof or wall sheathing. To combat this occurrence, insulation should be chosen that can help dissipate that moisture. CLIMATIZER PLUS™ is able to transport moisture to a surface where it can evaporate which is important for keeping moisture levels low and insulation effectiveness high, while preventing mould growth from forming on nearby building structures.

Installation Guide

Available for download on our website, or by request to info@climatizer.ca

Availability & Cost

CLIMATIZER PLUS™ cellulose insulation is available for shipping throughout Canada, the United States and Internationally. Please contact our Sales Representatives to receive additional information, pricing and delivery schedules. We offer high quality insulation material at competitive pricing for comparative performance features.

Warranty

CLIMATIZER PLUS™ is guaranteed to meet published specifications and standards., The applicator must warrant a specific product installation. Our warranty is available upon request.

Maintenance

CLIMATIZER PLUS™ requires no specific maintenance. A building owner should periodically inspect the installation to ensure that traffic has not displaced the insulation or disturbed the natural attic ventilation or permitted the insulation to contact heat sources.

Customer and Technical Support

Climatizer Insulation has a team of Sales. Customer Service Representatives, and technicians available to assist and advise you in addressing your insulation needs. Technical data and test reports are available upon request to assist designers and applicators in addressing project needs. Please reach out to Climatizer at info@climatizer.ca for more information.



CLIMATIZER INSULATION
Manufacturer of Cellulose Fiber for
Insulation and Infrastructure



climatizer.ca
info@climatizer.ca | orders@climatizer.ca
Canadian Owned, Canadian Made Since 1977